

MADE FROM  
**100%**  
RECYCLED  
FIBER

**PRODUCT SPECIFICATIONS**

**KRUGER PACKAGING**

**GreenWhite 161**

MILL CODE 08007

PROPERTY		UNITS	REJ MIN	TARGET	REJ MAX
BASIS WEIGHT		lbs/1000 ft <sup>2</sup>	32.8	33.0	38.9
BASIS WEIGHT		gsm	160	161	190
CALIPER		pt. (Tappi T 411)	—	7.9	—
CALIPER		µm (Tappi T 411)	—	200	—
MOISTURE		% (Tappi T 412)	5.5	7.0	8.5
BRIGHTNESS TOP		% (Tappi T 525)	71	74	77
A* TOP		% (Tappi T 527)	-0.2	0.8	1.8
b* TOP		% (Tappi T 527)	-2.8	-1.4	0.2
SHEFFIELD TOP		ml/min. (Tappi T 538)	—	200	—
COBB TOP	2 MIN.	gsm (Tappi T 441)	—	45	70
COBB BOTTOM	2 MIN.	gsm (Tappi T 441)	—	50	70
COBB TOP	30 MIN.	gsm (Tappi T 441)	—	100	110
SCOTT BOND CD		J/m <sup>2</sup> (Tappi T 569)	180	210	—
COMPRESSION, SCT, CD		kN/m (Tappi T 826)	—	2.5	—
WAX PICK		N# (Tappi T 459)	13	16	—
WAX Fluff		N# (Tappi T 459)	12	14	—

Optical Properties with a Color Touch 2 Spectrophotometer

Neutral Paper  
SFI Certified  
FSC Certifiable

Published date – April 14, 2025

Roll Finishing:

GreenWhite wound white side out  
Telescopic/Unequal winding: ±0.5 in.  
Cores: 4 in. Inside diam., 0,30 in. thick,  
Core Spec.: +1/16 in. to -1/4 in. Length  
Roll Width ±0.08 in.  
2 Straps: at 1.0 ±1/2 in. from roll edges

MADE FROM  
**100%**  
RECYCLED  
FIBER

**PRODUCT SPECIFICATIONS**

**KRUGER PACKAGING**

**GreenWhite 183**

MILL CODE 09007

PROPERTY		UNITS	REJ MIN	TARGET	REJ MAX
BASIS WEIGHT		lbs/1000 ft <sup>2</sup>	37.3	37.5	—
BASIS WEIGHT		gsm	182	183	—
CALIPER		pt. (Tappi T 411)	—	9.3	—
CALIPER		µm (Tappi T 411)	—	235	—
MOISTURE		% (Tappi T 412)	4.0	6.0	7.0
BRIGHTNESS TOP		% (Tappi T 525)	71	74	77
A* TOP		% (Tappi T 527)	-0.2	0.8	1.8
b* TOP		% (Tappi T 527)	-2.8	-1.4	0.2
SHEFFIELD TOP		ml/min. (Tappi T 538)	—	210	—
COBB TOP	2 MIN.	gsm (Tappi T 441)	—	45	70
COBB BOTTOM	2 MIN.	gsm (Tappi T 441)	—	50	70
COBB TOP	30 MIN.	gsm (Tappi T 441)	—	100	110
SCOTT BOND CD		J/m <sup>2</sup> (Tappi T 569)	180	210	—
COMPRESSION, SCT, CD		KN/m (Tappi T 826)	2.5	3.0	—
WAX PICK		N# (Tappi T 459)	13	16	—
WAX Fluff		N# (Tappi T 459)	12	14	—

Optical Properties with a Color Touch 2 Spectrophotometer

Neutral Paper  
SFI Certified  
FSC Certifiable

Published date – April 14, 2025

Roll Finishing:

GreenWhite wound white side out  
Telescopic/Unequal winding: ±0.5 in.  
Cores: 4 in. Inside diam., 0,30 in. thick,  
Core Spec.: +1/16 in. to -1/4 in. Length  
Roll Width ±0.08 in.  
2 Straps: at 1.0 ±1/2 in. from roll edges

MADE FROM  
**100%**  
RECYCLED  
FIBER

**PRODUCT SPECIFICATIONS**

**KRUGER PACKAGING**

**GreenWhite 205**

**MILL CODE** 10007

PROPERTY		UNITS	REJ MIN	TARGET	REJ MAX
BASIS WEIGHT		lbs/1000 ft <sup>2</sup>	41.8	42.0	45.1
BASIS WEIGHT		gsm	204	205	220
CALIPER		pt. (Tappi T 411)	—	10.0	—
CALIPER		µm (Tappi T 411)	—	253	—
MOISTURE		% (Tappi T 412)	4.0	6.5	8.0
BRIGHTNESS TOP		% (Tappi T 525)	71	74	77
A* TOP		% (Tappi T 527)	-0.2	0.8	1.8
b* TOP		% (Tappi T 527)	-2.8	-1.4	0.2
SHEFFIELD TOP		ml/min. (Tappi T 538)	—	220	—
COBB TOP	2 MIN.	gsm (Tappi T 441)	—	45	70
COBB BOTTOM	2 MIN.	gsm (Tappi T 441)	—	50	70
COBB TOP	30 MIN.	gsm (Tappi T 441)	—	100	110
SCOTT BOND CD		J/m <sup>2</sup> (Tappi T 569)	180	210	—
COMPRESSION, SCT, CD		kN/m (Tappi T 826)	3.1	3.3	—
WAX PICK		N# (Tappi T 459)	13	16	—
WAX Fluff		N# (Tappi T 459)	12	14	—

Optical Properties with a Color Touch 2 Spectrophometer

Neutral Paper  
SFI Certified  
FSC Certifiable

Published date – April 14, 2025

Roll Finishing:

GreenWhite wound white side out  
Telescopic/Unequal winding: ±0.5 in.  
Cores: 4 in. Inside diam., 0,30 in. thick,  
Core Spec.: +1/16 in. to -1/4 in. Length  
Roll Width±0.08 in.  
2 Straps: at 1.0 ±1/2 in. from roll edges

MADE FROM  
**100%**  
RECYCLED  
FIBER

**PRODUCT SPECIFICATIONS**

**KRUGER PACKAGING**

**GreenWhite 270**

**MILL CODE** 12707

PROPERTY		UNITS	REJ MIN	TARGET	REJ MAX
BASIS WEIGHT		lbs/1000 ft <sup>2</sup>	54.9	55.3	—
BASIS WEIGHT		gsm	268	270	—
CALIPER		pt. (Tappi T 411)	—	13.0	—
CALIPER		µm (Tappi T 411)	—	330	—
MOISTURE		% (Tappi T 412)	4.5	7.0	8.5
BRIGHTNESS TOP		% (Tappi T 525)	71	74	77
A* TOP		% (Tappi T 527)	-0.2	0.8	1.8
b* TOP		% (Tappi T 527)	-2.8	-1.4	0.2
SHEFFIELD TOP		ml/min. (Tappi T 538)	—	250	—
COBB TOP	2 MIN.	gsm (Tappi T 441)	—	45	70
COBB BOTTOM	2 MIN.	gsm (Tappi T 441)	—	50	70
COBB TOP	30 MIN.	gsm (Tappi T 441)	—	100	110
SCOTT BOND CD		J/m <sup>2</sup> (Tappi T 569)	180	210	—
COMPRESSION, SCT, CD		kN/m (Tappi T 826)	4.25	4.8	—
WAX PICK		N# (Tappi T 459)	13	16	—
WAX Fluff		N# (Tappi T 459)	12	14	—

Optical Properties with a Color Touch 2 Spectrophotometer

Neutral Paper  
SFI Certified  
FSC Certifiable

Published date – April 14, 2025

Roll Finishing:

GreenWhite wound white side out  
Telescopic/Unequal winding: ±0.5 in.  
Cores: 4 in. Inside diam., 0,30 in. thick,  
Core Spec.: +1/16 in. to -1/4 in. Length  
Roll Width ±0.08 in.  
2 Straps: at 1.0 ±1/2 in. from roll edges