



MADE FROM
100%
RECYCLED
FIBER

PRODUCT SPECIFICATIONS

KRUGER PACKAGING

GreenWhite 161

MILL CODE 08007

PROPERTY	UNITS	REJ MIN	TARGET	REJ MAX
BASIS WEIGHT	lbs/1000 ft ²	32.8	33.0	38.9
BASIS WEIGHT	gsm	160	161	190
CALIPER	pt. (Tappi T 411)	—	7.9	—
CALIPER	μm (Tappi T 411)	—	200	—
MOISTURE	% (Tappi T 412)	5.5	7.0	8.5
BRIGHTNESS TOP	% (Tappi T 525)	71	74	77
A* TOP	% (Tappi T 527)	-0.2	0.8	1.8
b* TOP	% (Tappi T 527)	-2.8	-1.4	0.2
SHEFFIELD TOP	ml/min. (Tappi T 538)	—	200	—
COBB TOP 2 MIN.	gsm (Tappi T 441)	—	45	70
COBB BOTTOM 2 MIN.	gsm (Tappi T 441)	—	50	70
COBB TOP 30 MIN.	gsm (Tappi T 441)	—	100	110
SCOTT BOND CD	J/m ² (Tappi T 569)	180	210	—
COMPRESSION, SCT, CD	kN/m (Tappi T 826)	—	2.5	—
WAX PICK	N# (Tappi T 459)	13	16	—
WAX Fluff	N# (Tappi T 459)	12	14	—

Optical Properties with a Color Touch 2 Spectrophotometer

Neutral Paper
SFI Certified
FSC Certifiable

Published date – June 12, 2025

Roll Finishing:

GreenWhite wound white side out
Telescopic/Unequal winding: ±0.5 in.
Cores: 4 in. Inside diam., 0,30 in. thick,
Core Spec.: +1/16 in. to -1/4 in. Length
Roll Width ±0.08 in.
2 Straps: at 1.0 ± 1/2 in. from roll edges



MADE FROM
100%
RECYCLED
FIBER

PRODUCT SPECIFICATIONS

KRUGER PACKAGING

GreenWhite 183

MILL CODE 09007

PROPERTY	UNITS	REJ MIN	TARGET	REJ MAX
BASIS WEIGHT	lbs/1000 ft ²	37.3	37.5	—
BASIS WEIGHT	gsm	182	183	—
CALIPER	pt. (Tappi T 411)	—	9.3	—
CALIPER	μm (Tappi T 411)	—	235	—
MOISTURE	% (Tappi T 412)	4.0	6.0	7.0
BRIGHTNESS TOP	% (Tappi T 525)	71	74	77
A* TOP	% (Tappi T 527)	-0.2	0.8	1.8
b* TOP	% (Tappi T 527)	-2.8	-1.4	0.2
SHEFFIELD TOP	ml/min. (Tappi T 538)	—	210	—
COBB TOP 2 MIN.	gsm (Tappi T 441)	—	45	70
COBB BOTTOM 2 MIN.	gsm (Tappi T 441)	—	50	70
COBB TOP 30 MIN.	gsm (Tappi T 441)	—	100	110
SCOTT BOND CD	J/m ² (Tappi T 569)	180	210	—
COMPRESSION, SCT, CD	kN/m (Tappi T 826)	2.5	3.0	—
WAX PICK	N# (Tappi T 459)	13	16	—
WAX Fluff	N# (Tappi T 459)	12	14	—

Optical Properties with a Color Touch 2 Spectrophotometer

Neutral Paper
SFI Certified
FSC Certifiable

Published date – June 12, 2025

Roll Finishing:

GreenWhite wound white side out
Telescopic/Unequal winding: ±0.5 in.
Cores: 4 in. Inside diam., 0,30 in. thick,
Core Spec.: +1/16 in. to -1/4 in. Length
Roll Width ±0.08 in.
2 Straps: at 1.0 ±1/2 in. from roll edges



MADE FROM
100%
RECYCLED
FIBER

PRODUCT SPECIFICATIONS

KRUGER PACKAGING

GreenWhite 205

MILL CODE 10007

PROPERTY	UNITS	REJ MIN	TARGET	REJ MAX
BASIS WEIGHT	lbs/1000 ft ²	41.8	42.0	45.1
BASIS WEIGHT	gsm	204	205	220
CALIPER	pt. (Tappi T 411)	—	10.0	—
CALIPER	μm (Tappi T 411)	—	253	—
MOISTURE	% (Tappi T 412)	4.0	6.5	8.0
BRIGHTNESS TOP	% (Tappi T 525)	71	74	77
A* TOP	% (Tappi T 527)	-0.2	0.8	1.8
b* TOP	% (Tappi T 527)	-2.8	-1.4	0.2
SHEFFIELD TOP	ml/min. (Tappi T 538)	—	220	—
COBB TOP 2 MIN.	gsm (Tappi T 441)	—	45	70
COBB BOTTOM 2 MIN.	gsm (Tappi T 441)	—	50	70
COBB TOP 30 MIN.	gsm (Tappi T 441)	—	100	110
SCOTT BOND CD	J/m ² (Tappi T 569)	180	210	—
COMPRESSION, SCT, CD	kN/m (Tappi T 826)	3.1	3.3	—
WAX PICK	N# (Tappi T 459)	13	16	—
WAX Fluff	N# (Tappi T 459)	12	14	—

Optical Properties with a Color Touch 2 Spectrophotometer

Neutral Paper
SFI Certified
FSC Certifiable

Published date – June 12, 2025

Roll Finishing:

GreenWhite wound white side out
Telescopic/Unequal winding: ±0.5 in.
Cores: 4 in. Inside diam., 0,30 in. thick,
Core Spec.: +1/16 in. to -1/4 in. Length
Roll Width ±0.08 in.
2 Straps: at 1.0 ±1/2 in. from roll edges



MADE FROM
100%
RECYCLED
FIBER

PRODUCT SPECIFICATIONS

KRUGER PACKAGING

GreenWhite 270

MILL CODE 12707

PROPERTY	UNITS	REJ MIN	TARGET	REJ MAX
BASIS WEIGHT	lbs/1000 ft ²	54.9	55.3	—
BASIS WEIGHT	gsm	268	270	—
CALIPER	pt. (Tappi T 411)	—	13.0	—
CALIPER	μm (Tappi T 411)	—	330	—
MOISTURE	% (Tappi T 412)	4.5	7.0	8.5
BRIGHTNESS TOP	% (Tappi T 525)	71	74	77
A* TOP	% (Tappi T 527)	-0.2	0.8	1.8
b* TOP	% (Tappi T 527)	-2.8	-1.4	0.2
SHEFFIELD TOP	ml/min. (Tappi T 538)	—	250	—
COBB TOP 2 MIN.	gsm (Tappi T 441)	—	45	70
COBB BOTTOM 2 MIN.	gsm (Tappi T 441)	—	50	70
COBB TOP 30 MIN.	gsm (Tappi T 441)	—	100	110
SCOTT BOND CD	J/m ² (Tappi T 569)	180	210	—
COMPRESSION, SCT, CD	kN/m (Tappi T 826)	4.25	4.8	—
WAX PICK	N# (Tappi T 459)	13	16	—
WAX Fluff	N# (Tappi T 459)	12	14	—

Optical Properties with a Color Touch 2 Spectrophotometer

Neutral Paper
SFI Certified
FSC Certifiable

Published date – June 12, 2025

Roll Finishing:

GreenWhite wound white side out
Telescopic/Unequal winding: ±0.5 in.
Cores: 4 in. Inside diam., 0,30 in. thick,
Core Spec.: +1/16 in. to -1/4 in. Length
Roll Width ±0.08 in.
2 Straps: at 1.0 ± 1/2 in. from roll edges